



Pearl River Lock Chamber.
Poly Armor test areas on
Sheet pile walls



Topcoat could be easily stripped
from primer in test areas with
White Metal Grade surface
preparation.



Coating had very poor adhesion
to test areas with Commercial
Grade surface preparation. On
some areas the coating was gone
after only 4 months.