

Paint Testing Report

Manufacturer:
DeVoe Coatings Company
4000 DuPont Circle
Louisville, KY 40207

Testing Laboratory:
U. S. Army CERL
ATTN: CECER-CF-M
P. O. Box 9005
Champaign, IL 61826-9005

Product Designation:
Bar Rust 239

Sample Designation:
Lab report 95L184

Specification: CID A-A-3127
Date: 18 OCT 95

Analysis:	Min	Max	Result	Pass
Condition in container			OK	YES
Application properties, spray:			OK	YES
Application properties, roller:			OK	YES
Prohibited Materials Lead,		0.06	ND	YES
Prohibited Materials (See Spec.)		0.1	ND	YES
Dry Hard Time (Hours)		16	OK	YES
Pot Life (Hours)	3		>3	YES
Intercoat Adhesion			OK	YES
VOC as applied (g/L)		350	86	YES
Accelerated Corrosion Resistance (4032 Hours)				
Blistering at Scribe at 2688 hours		1	0	YES
Blistering at Scribe at 3360 hours		4	2	YES
Blistering at Scribe (Average Rating)	6.5		7.3	YES
Other blistering on panels		None	None	YES
Rust rating, ASTM D 610 (Average Rating)	9.0		9.3	YES
Rust Undercutting (Max.)	6.0		6.0	YES
Rust Undercutting (Average Rating)	6.0		6.8	YES
Composite of averages (Rust + Blister + Undercut)	23.0		23.5	YES

Sample meets all specification requirements? YES NO

Remarks:

Signature: