

### Paint Testing Report

**Manufacturer:**  
International/Courtaulds Coatings  
6001 Antoine  
Houston, TX 77210-4806

**Testing Laboratory:**  
U. S. Army CERL  
ATTN: CECER-CF-M  
P. O. Box 9005  
Champaign, IL 61826-9005

**Product Designation:**  
Interguard H.S. Universal Epoxy  
Interthane

**Sample Designation:**  
Lab report 95L188

**Specification:** CID A-A-3132  
**Date:** 18 OCT 95

Analysis:	Min	Max	Result	Pass
Condition in container			OK	YES
Application properties, spray:			OK	YES
Application properties, roller:			OK	YES
Prohibited Materials Lead,		0.06	ND	YES
Prohibited Materials (See Spec.)		0.1	ND	YES
Dry Hard Time (Hours) Primer		8	< 8	YES
Topcoat		6	< 6	YES
Pot Life (Hours) Primer	4		> 4	YES
Topcoat	4		> 4	YES
Intercoat Adhesion			OK	YES
VOC as applied (g/L) Primer		350	192	YES
Topcoat		420	414	YES
<b>Accelerated Corrosion Resistance (4032 Hours)</b>				
Blistering at Scribe at 1344 hours (Panels)		2	0	YES
Blistering at Scribe at 2016 hours (Panels)		2	0	YES
Blistering at Scribe at 2688 hours (Panels)		4	2	YES
Blistering at Scribe at 3360 hours (Panels)		4	2	YES
Blister rating at Scribe at 4032 hours (Average)	8		9.0	YES
Other blistering on Panels		None	None	YES
Rust Undercutting at Scribe(Single panel Rating)	5		8	YES
Rust Undercutting at scribe (Average of 6,Rating)	7		9.0	YES
Other rusting on panels (Rating)	10		10	YES
Composite of averages (Rust + Blister + Undercut)	25		28.0	YES
Sample meets all specification requirements?	YES	<input checked="" type="checkbox"/>	NO	<input type="checkbox"/>
Remarks:				
Signature:				